


Transparent Tape Film

11T 25μm

Technical Data

Structure



Description

Transparent film with high coefficient of friction, featuring inner-side corona treatment to enhance surface energy and adhesion for improved printability and lamination.

Application

Widely used as a base film for adhesive tapes, offering excellent dimensional stability, surface treatment, and compatibility with various adhesive systems.

| Properties | Ref. | Units | ASTM #/ Test Method | 11T | | | | | | | | | | |
|----------------------------------|-------|-------------------------|------------------------|-----------|-------|-------|-----------|-------|-------|-----------|-------|-------|-----------|-------|
| Physical Data | | | | | | | | | | | | | | |
| Average Thickness | | micron | D-374-C | 18 | 20 | 23 | 24 | 25 | 28 | 29 | 30 | 40 | 45 | 50 |
| | | gauge | | 71 | 79 | 90 | 94 | 98 | 110 | 114 | 118 | 157 | 177 | 197 |
| | | mils | | 0.7 | 0.8 | 0.9 | 0.9 | 1.0 | 1.1 | 1.1 | 1.2 | 1.6 | 1.8 | 2.0 |
| Thickness Variation | | %(±) | | 3 | | | | | | | | | | |
| Density | | g/cc | | 0.910 | | | | | | | | | | |
| Average Substance | | g/m | | 16.3 | 18.1 | 20.8 | 21.7 | 22.6 | 25.3 | 26.2 | 27.2 | 36.2 | 40.7 | 45.3 |
| Surface tension(min) | | dynes/cm | D-2578 | ≥38 | | | | | | | | | | |
| Kinetic COF | UT-UT | | D-1894 | 0.4-0.6 | | | | | | | | | | |
| Yield | | m ² /Kg | D-4321 | 61.4 | 55.2 | 48.0 | 46.0 | 44.2 | 39.5 | 38.1 | 36.8 | 27.6 | 24.6 | 22.1 |
| | | in ² /lb | D-4321 | 43160 | 38844 | 33777 | 32370 | 31075 | 27745 | 26789 | 25896 | 19422 | 17264 | 15537 |
| Optical Data | | | | | | | | | | | | | | |
| Gloss(45) | | gardner | D-2457 | ≥95 | | | | | | | | | | |
| Haze | | % | D-1003 | ≤2.0 | | | | | | | | | | |
| Mechanical Data | | | | | | | | | | | | | | |
| Tensile Strength | MD | kg/cm | D-882 | 120-160 | | | | | | | | | | |
| | TD | | | 250-350 | | | | | | | | | | |
| Elongation at break | MD | % | D-882 | 150-170 | | | | | | | | | | |
| | TD | | | 50-65 | | | | | | | | | | |
| Thermal Data | | | | | | | | | | | | | | |
| Shrinkage (120°C/248F,5 min.) | MD | % | D-1204 | 2.0-4.0 | | | | | | | | | | |
| | TD | | | 1.0-2.0 | | | | | | | | | | |
| HotTack Strength | | g/15mm | @125°C @257°F | 330 | | | 350 | | | 380 | | | | |
| Barrier Data | | | | | | | | | | | | | | |
| MVTR(38°C,90%RH) | | g/(m ² ·day) | F-1249 | 4.0~5.4 | | | 3.0~4.3 | | | 2.5~4.0 | | | 1.2~3.5 | |
| MVTR(10B,90%RH) | | g/100i/day | | 0.26~0.35 | | | 0.19~0.26 | | | 0.16~0.26 | | | 0.08~0.23 | |

The values given in the above table are typical performance data for reference only.
If you have special requirements for product performance indexes, please communicate with business manager.

FOROP Advanced Materials Co., Ltd.

Address: No.166 Fuju Road, Yinxi Street, Fuqing City, Fuzhou City, Fujian Province, China

Email: sales@sino-forop.com | <https://sales.forop.com>

Update date:08/25