


Transparent Tape Film

11T 50 μ m

Structure



Description

Transparent film with high coefficient of friction, featuring inner-side corona treatment to enhance surface energy and adhesion for improved printability and lamination.

Application

Widely used as a base film for adhesive tapes, offering excellent dimensional stability, surface treatment, and compatibility with various adhesive systems.

Technical Data

Properties	Ref.	Units	ASTM #/ Test Method	11T											
Physical Data															
Average Thickness		micron	D-374-C	18	20	23	24	25	28	29	30	40	45	50	
		gauge		71	79	90	94	98	110	114	118	157	177	197	
		mils		0.7	0.8	0.9	0.9	1.0	1.1	1.1	1.2	1.6	1.8	2.0	
Thickness Variation		%(\pm)		3											
Density		g/cc		0.910											
Average Substance		g/m		16.3	18.1	20.8	21.7	22.6	25.3	26.2	27.2	36.2	40.7	45.3	
Surface tension(min)		dynes/cm	D-2578	\geq 38											
Kinetic COF	UT-UT		D-1894	0.4-0.6											
Yield		m ² /Kg	D-4321	61.4	55.2	48.0	46.0	44.2	39.5	38.1	36.8	27.6	24.6	22.1	
		in ² /lb	D-4321	43160	38844	33777	32370	31075	27745	26789	25896	19422	17264	15537	
Optical Data															
Gloss(45)		gardner	D-2457	\geq 95											
Haze		%	D-1003	\leq 2.0											
Mechanical Data															
Tensile Strength	MD	kg/cm	D-882	120-160											
	TD			250-350											
Elongation at break	MD	%	D-882	150-170											
	TD			50-65											
Thermal Data															
Shrinkage (120 $^{\circ}$ C/248F,5 min.)	MD	%	D-1204	2.0-4.0											
	TD			1.0-2.0											
HotTack Strength		g/15mm	@125 $^{\circ}$ C @257 $^{\circ}$ F	330			350			380					
Barrier Data															
MVTR(38 $^{\circ}$ C,90%RH)		g/(m ² ·day)	F-1249	4.0~5.4			3.0~4.3			2.5~4.0			1.2~3.5		
MVTR(10B,90%RH)		g/100i/day		0.26~0.35			0.19~0.26			0.16~0.26			0.08~0.23		

The values given in the above table are typical performance data for reference only.
If you have special requirements for product performance indexes, please communicate with business manager.

FOROP Advanced Materials Co., Ltd.

Address: No.166 Fuju Road, Yinxi Street, Fuqing City, Fuzhou City, Fujian Province, China

Email: sales@sino-forop.com | <https://sales.forop.com>

Update date:08/25